

PHILLYSTRAN® 12 STRAND BRAIDS TECNHORA® (ARAMID)

PART NUMBER	BREAK STRENGTH		DIAMETER		WEIGHT	
	lb	kN	in	mm	lb/1000 ft	kg/km
BR 10000T	10,000	45	1/4	6.4	21.5	32
BR 14000T	14,000	62	5/16	7.9	30.8	46
BR 20000T	20,000	89	3/8	9.5	43.1	64
BR 26000T	26,000	116	7/16	11.1	58.5	87
BR 35000T	35,000	156	1/2	12.7	77	115
BR 42000T	42,000	187	9/16	14.3	99	147
BR 52000T	52,000	231	5/8	15.9	120	179
BR 77000T	77,000	343	3/4	19.1	166.2	247
BR 125000T	125,000	556	1	25.4	301.6	449

Weights and dimensions can vary
Technora® is a Registered Trademark of Teijin Twaron B.V. LTD

CAUTION:

Break Strength: The breaking strength of a rope is the load at which a new rope will break when tested under laboratory conditions. Break strength should not be mistaken for safe working load. **Safe Working Load:** Because of the wide range of rope use, rope condition and the degree of risk of life or property, it is not possible to make a blanket recommendation for safe working load. It is ultimately dependent on the rope user to determine what percentage of break strength is their own safe working load. **Wear:** Ropes wear out with use; the more severe the usage, the greater the wear. It is often not possible to detect wear on a rope by visible signs alone. Therefore, it is recommended that the rope user determine a retirement criteria for ropes in their application. For assistance in developing safe working load and retirement criteria for each application please call or write Phillystran.

All printed statements, data and recommendations are based on reliable information and tests, and are presented without any guarantee or warranty. Statements regarding the use of Phillystran's products and processes are not to be construed as recommendations for use in violation of any applicable laws, regulations or patent rights. © All rights reserved.

